

**Original citation:**

Zhang, G.H. and Zhao, C.Y. (2011). Thermal and rheological properties of microencapsulated phase change materials. *Renewable Energy*, 36(11), pp. 2959-2966.

**Permanent WRAP url:**

<http://wrap.warwick.ac.uk/35608>

**Copyright and reuse:**

The Warwick Research Archive Portal (WRAP) makes the work of researchers of the University of Warwick available open access under the following conditions. Copyright © and all moral rights to the version of the paper presented here belong to the individual author(s) and/or other copyright owners. To the extent reasonable and practicable the material made available in WRAP has been checked for eligibility before being made available.

Copies of full items can be used for personal research or study, educational, or not-for-profit purposes without prior permission or charge. Provided that the authors, title and full bibliographic details are credited, a hyperlink and/or URL is given for the original metadata page and the content is not changed in any way.

**Publisher's statement:**

"NOTICE: this is the author's version of a work that was accepted for publication in *Renewable Energy*. Changes resulting from the publishing process, such as peer review, editing, corrections, structural formatting, and other quality control mechanisms may not be reflected in this document. Changes may have been made to this work since it was submitted for publication. A definitive version was subsequently published in *Renewable Energy*, [VOL:36, ISSUE:11, November 2011 DOI: 10.1016/j.renene.2011.04.002"]

**A note on versions:**

The version presented here may differ from the published version or, version of record, if you wish to cite this item you are advised to consult the publisher's version. Please see the 'permanent WRAP url' above for details on accessing the published version and note that access may require a subscription.

For more information, please contact the WRAP Team at: [wrap@warwick.ac.uk](mailto:wrap@warwick.ac.uk)



<http://go.warwick.ac.uk/lib-publications>

# Thermal and Rheological Properties of Microencapsulated Phase Change Materials

G. H. Zhang, C. Y. Zhao\*

*School of Engineering, University of Warwick, Coventry, CV4 7AL, UK*

---

## Abstract

The use of microencapsulated phase change materials (MPCMs) is one of the most efficient ways of storing thermal energy. When the microencapsulated phase change material (MPCM) is dispersed into the carrier fluid, microencapsulated phase change slurry (MPCS) is prepared. Due to the relatively large surface area to volume MPCM and its large apparent specific heat during the phase change period, better heat transfer performance can be achieved. Therefore, MPCS can be used as both the energy storage and heat transfer media.

This paper studies the thermal and rheological properties of a series of prepared MPCS. In the experiment: MPCS fabricated by dispersing MPCM into water with an appropriate amount of surfactant. **The mass ratio of MEPCM to water and surfactant was 10:90:1, 25:75:1, 35:65:1 in prepared MPCS samples, respectively.** Then the thermal conductivity and specific heat of MPCS were measured by the Hot Disk. The melting/crystallizing temperature and fusion heat/crystallization heat of the phase change materials were obtained from a DSC (differential scanning calorimetry) during the heating/cooling process. Physical properties, such as viscosity, diameter and its size distribution of MPCS were investigated by a rheometer and a particle characterization system. Meanwhile, the chemical structure of the sample was analysed using Fourier Transformed Infrared spectroscopy (FTIR).

**The results showed that the thermal conductivity and the specific heat of MPCS decrease with particle concentration for the temperatures below the melting point. Overall, the MPCS can be considered as Newtonian fluid within the test region (shear rate  $>200\text{ s}^{-1}$  and mass fraction  $<0.35$ ). The viscosity is higher for bigger particle slurries.** The findings of the work lead to the conclusion that the present work suggested that MEPCMs can be used in “passive” applications or in combination with active cooling systems; and it also provided a new understanding for fabricating microencapsulated phase change slurry, it is for sure that to have a better potential for energy storage. Accordingly, it has demonstrated that the MPCS fabricated in the current research are suitable for potential application as heat transfer media in the thermal energy storage.

*Keywords:* MPCM; MPCS; Thermal properties; Rheological Properties, Heat transfer

---

\* Corresponding author. Tel.: +44 (0) 24-76522339.

E-mail address: [C.Y.Zhao@warwick.ac.uk](mailto:C.Y.Zhao@warwick.ac.uk); [changing.zhao@gmail.com](mailto:changing.zhao@gmail.com) (C. Y. ZHAO)

## Nomenclature

$C_p$	specific heat capacity (kJ/ (kg °C))
$d, D$	diameter (m)
$\Delta H_c$	heat of crystallization (kJ/kg)
$\Delta H_f$	heat of fusion (kJ/kg)
$k$	Thermal conductivity (W/(m °C) )
$m$	mass (kg)
$T_m$	melting temperature (°C)
$T_c$	crystallizing temperature (°C)
$W$	mass fraction (-)
<i>Greek letters</i>	
$\rho$	density (kg/m <sup>3</sup> )
$\Phi$	the encapsulation efficiency (%)
$\mu$	viscosity (Pa s)
<i>Subscripts</i>	
b	bulk
c	microcapsule core
f	fluid
p	particle
w	wall, water

## 1. Introduction

Phase change materials (PCMs) have long been used for thermal energy storage due to the large amount of heat absorption/release while undergoing phase changes, with only small temperature variations [1-10]. Organic and inorganic materials are two most common groups of PCMs [11]. Organic materials are further described as paraffin and non-paraffin. Most organic PCMs are non-corrosive and chemically stable, and have little or no sub-cooling. They are compatible with most building materials and have a high latent heat per unit weight and low vapour pressure. But they also have disadvantages in low thermal conductivities, high changes in volume on phase change and flammability. In contrast, inorganic materials (salt hydrate and metallic) have a high latent heat per unit volume and high thermal conductivities, and are non-flammable and low in cost in comparison to organic materials. However, they are corrosive to most metals and suffer from decomposition and sub-cooling, which can affect their phase change properties. Therefore, In order to overcome these problems, a new technique of utilising microencapsulated phase change material (MEPCM) in thermal energy storage system has been developed. Microencapsulated PCMs provide a means to solve the super-cooling problem and interfacial combination with the circumstance materials [12]. The main merits of microencapsulated phase change material (MPCM) over PCM are as follows: (1) increasing heat transfer area; (2) reducing PCMs reactivity towards the outside environment and controlling the changes in the storage material volume as phase change occurs. The use of microencapsulated phase change materials (MPCMs) is one of the most efficient ways of storing thermal energy and it has received a growing attention in the past decade [12-27]. Since MPCM was developed, it had been mainly used in the textile [19, 28-31] and building applications [32-36].

Due to the low thermal conductivity of PCMs [10], a new approach was proposed to improve the thermal performance of the thermal system (e.g. the secondary refrigeration and air conditioning loops ). When the MPCM is dispersed into the carrier fluid, e.g. water, a kind of suspension named as microencapsulated phase change material slurry (MPCS) is formed [37]. Water is normally used as the carrier fluid since it has no obvious negative effect on fabricating MPCS and is cheap to get, although the carrier fluid should have a high thermal conductivity and a large specific heat capacity. In comparison of conventional phase change material slurries (PCS),

better heat transfer performance can be achieved due to the relatively large surface area to volume of MPCM. Therefore, it can be used as both thermal energy storage and heat transfer media [38-43]. The thermal and physical properties of MPCM are crucial for the MPCM system design, and they are very different from those of the MPCM materials and carrier fluids. These mainly include the thermal conductivity, viscosity and specific heat. The optimum design of thermal energy storage systems, which run with microencapsulated phase change material slurry, requires a good knowledge of flow and heat transfer characteristics of two-phase slurry involved in phase change, in order to reduce the capital cost, system size, and energy consumption [44].

The purpose of this study is to investigate the thermal and rheological properties of the MPCMs. In this paper, a series of MPCM were prepared for experimental test. The chemical structure, morphology, microstructure, diameter and its size distribution, thermal properties of the MPCMs and rheological properties of MPCM were obtained from experimental measurements.

## **2. Experimental test**

### *2.1 Investigated materials*

- DPNT06-0182 (Ciba Specialty Chemicals, UK), properties of microcapsule as given by the manufacture: it comprises 87.5% paraffin wax and 12.5% crosslinked acrylic polymer shell (core/shell ratio: 87.5:12.5).
- Micronal<sup>®</sup> DS 5008X (BASF, Germany), properties of microcapsule as given by the manufacture: it comprises a paraffin mixture and highly crosslinked polymethyl methacrylate (PMMA) shell; formaldehyde-free (core/shell ratio: 7:3).

### *2.2 Chemical composite analysis*

The chemical structure was analyzed using PerkinElmer-Spectrum 100 Fourier transformed infrared spectroscopy (FTIR) with the KBr sampling method.

### 2.3 Surface morphology and structure of microcapsules

Morphologies were obtained by using a Cambridge instruments-STEREOSCAN 90 scanning electron microscopy (SEM). A Reichert Jung-Polyvar MET optical phase-contrast microscope was employed to investigate the microstructure of the microcapsules.

### 2.4 Diameter measurement

The microcapsules size distribution from light diffraction was performed using a Malvern Instruments-Hydro 2000S laser particle size analyzer, and the mean diameters of the microcapsules were determined.

### 2.5 Thermal properties of microcapsules

Differential scanning calorimetry (DSC) was performed to determine the melting temperature and heat of fusion during the heating process, crystallizing temperature and crystallization heat during the cooling process by using a SETARAM Instrumentation-D/SENSYS-2A differential scanning calorimeter, and all measurements were carried out under an air atmosphere at a heating or cooling rate of 0.2 °C/min. Thermal gravimetry (TG) analysis was applied to measure the thermal stability of these microcapsules by a Polymer laboratories-STA 1500. The Thermal conductivity and specific heat of the MPCMs and MPCS were tested by using a HotDisk Instruments-TPS 2500S. The following sets of thermal property models that used by previous researchers to MPCS were employed in this study.

The density & specific heat of the microcapsules and the specific heat of MPCS were calculated using mass and energy balance [38]:

$$\rho_p = \frac{\text{Microcapsule mass}}{\text{Core mass}} \left(\frac{d_c}{d_p}\right)^3 \rho_c \quad (1)$$

$$C_{p,p} = \frac{\text{Core mass} \cdot C_c + \text{Shell mass} \cdot C_w}{\text{Shell mass} \cdot \rho_c + \text{Core mass} \cdot \rho_w} \frac{\rho_c \rho_w}{\rho_p} \quad (2)$$

$$C_{p,b} = W_p C_{p,p} + W_w C_{p,w} \quad (3)$$

The thermal conductivity of the microcapsule was calculated using the composite sphere approach [9]:

$$\frac{1}{k_p d_p} = \frac{1}{k_c d_c} + \frac{d_p - d_c}{k_w d_p d_c} \quad (4)$$

The thermal conductivity of MPCs was calculated by Maxwell's relation [27]:

$$k_b = \frac{2k_f + k_p + 2W(k_p - k_f)}{2k_f + k_p - W(k_p - k_f)} \quad (5)$$

## 2.6 Rheology measurement

Rheological properties were measured by a rheometer (Malvern Instruments-Kinexus Ultra). Three kinds of MPCs were prepared for each sample with the mass ratio of MEPCM to water and surfactant: 10:90:1, 25:75:1, 35:65:1, respectively. The experiments were conducted at four different temperatures (below and above the melting temperature) for each MPCs.

## 3. Results and discussions

### 3.1 Microencapsulated phase change material

The FTIR spectra of the microcapsules (DPNT06-0182, CIBA) are presented in Fig. 1. The alkyl C-H stretching vibrations are found around  $2900 \text{ cm}^{-1}$ . C-H stretching peaks of crosslinked acrylic polymer are found around  $1715 \text{ cm}^{-1}$ . The peak at  $1466 \text{ cm}^{-1}$  is due to C-H bending and the peaks at  $1170 \text{ cm}^{-1}$  can be assigned to the C-O stretching of the ester group. FTIR spectra show both characteristic peaks of crosslinked acrylic polymer and paraffin wax. Fig. 2 shows the FTIR spectra of the microcapsules (DS 5008X BASF). The strong alkyl C-H stretching vibrations are found around  $2950 \text{ cm}^{-1}$ . C-H stretching peaks of PMMA are found around  $1730 \text{ cm}^{-1}$ . The peak at  $1463 \text{ cm}^{-1}$  is due to C-H bending and the peaks at  $1116 \text{ cm}^{-1}$  is associated with the C-O stretching of the ester group. The spectra of the microcapsules show both characteristic peaks of PMMA and paraffin mixture.

Fig. 3 shows the SEM images of the CIBA microcapsules with various diameters. The diameters of sample are in the range of 10 - 100  $\mu\text{m}$ . It is observed that the most of the microcapsules have regularly spherical shape and smooth surface. The surfaces of the microcapsules are compact without any disfigurement on the shells of microcapsules.

However, dimples exist on some of the microcapsules due to the volume contracting as paraffin crystallized. Similar SEM images of the BASF microcapsules are also examined (not shown here). Fig. 4 shows the optical phase-contrast micrographs of the CIBA microcapsules. An obvious core-shell microstructure can be distinguished from Fig. 4, where the bright circle layer representing the shell around the droplets is visible, and a core capsule of the paraffin mixture with dark colour is obvious within the microcapsule. These microcapsules exhibit a regularly spherical shape without any obvious disfigurement on their surfaces. Zhang et al. [18] indicated that morphology of the microcapsules was greatly influenced by the stirring rate, emulsifier content during the fabrication process.

The particle size distribution (PSD) of the CIBA microcapsules is shown in Fig. 5(a). The PSD in volume shows multimodal distributions of particle sizes ranging in the interval between 0.7 and 700  $\mu\text{m}$ . However, the most of particle sizes are in the size range from 10 to 100  $\mu\text{m}$ . The average diameter of microcapsules was 40  $\mu\text{m}$ . Fig. 5(b) shows the PSD of the BASF microcapsules, the agglomerated secondary particles of the powder can disintegrate under the effect of water. As it can see from Fig. 5(b), the PSD in volume shows unimodal distributions of particle sizes ranging from 1 to 20  $\mu\text{m}$  and the average diameter of microcapsules was 7  $\mu\text{m}$ . The stirring rate and emulsifier content have great effect on particle size distribution [18].

The thermal properties of the microcapsules of CIBA & BASF and the thermal properties of the MPCS of CIBA were measured by DSC, and their thermograms are presented in Figs. 6(a), 6(b) and 6(c), respectively, and the melting and crystallization properties of all samples are summarized in Table 1. It shows that there is only one peak appearing in the DSC heating thermograms for both samples. However, it is also found from Fig. 6(a) that two distinct peaks appear in the cooling thermograms of the CIBA microcapsules. Zhang et al. [45] indicated that the multiple peaks behavior on the DSC cooling curves are not caused by the difference of the cooling rates in the measured range and they are mainly caused by the difference in the average diameter. A similar cooling behaviour has been described for similar microencapsulated PCM systems in which the supercooling crystallization phenomena occurred when the diameter of microcapsules was smaller than 100  $\mu\text{m}$ [12], the authors stated that during the crystallization of the paraffin mixture, the peak  $\alpha$  is attributed to the

heterogeneously nucleated liquid-rotator transition, which may be due to the crystallization of paraffin mixture on the inner wall of the microcapsules, and the peak  $\beta$  is attributed to the homogeneously nucleated liquid-crystal transition. Yamagishi et al. [40] indicated that the supercooling crystallization was caused by the decrease in the number of nuclei in each microcapsule due to the reduced diameter. Fig. 6(c) shows that all three thermograms of the MPCs of CIBA samples present very similar melting temperature and crystallizing temperature to the MPCM of CIBA. However, the heat of fusion and the heat of crystallization of the MPCs were smaller than MPCM due to the addition of water changes the latent heat storage capacity of MPCMS, and they are increasing gradually with the mass concentration of MPCs. Overall, the phase change properties of the microcapsules are mainly described with two important parameters, encapsulated efficiency ( $\Phi$ ) and phase change temperature,  $T_c$  and  $T_m$ . Especially, the heat of fusion of the microcapsules affecting the working effect of the MPCM that strongly depends on the encapsulated efficiency. Figs. 7(a) and 7(b) shows the weight loss percentage of the microcapsules with CIBA sample and BASF sample, respectively. It is notable that the CIBA sample has relatively better thermal stability than the BASF sample.

### *3.2 Microencapsulated phase change material slurries*

Figs. 8 and 9 show the effect of concentration (wt %) on the thermal conductivity and the specific heat of the MPCs, respectively, for CIBA and BASF products. The results show that the thermal conductivity and specific heat decrease with the increase of concentration due to the lower thermal conductivities and specific heat of the particles compared to the base fluid, water. Overall, the prediction agrees with the experimental data fairly well. It should be pointed out that the experimental test was carried out at the temperatures below the melting point of the PCMs inside the particles. For the case above the melting temperature of PCMs, the story may be different due to the phase change, and this warrants a further study for this problem in the future.

The rheological behaviors of the prepared MPCs with the mass concentration varying from 10%, 25% and 35% were measured by Kinexus Ultra Rheometer (Malvern Instruments Ltd), respectively. The results showed that the shear stress linearly increases with shear rate for 10% and 25% cases, therefore the slurry with

concentration below 25% can be considered as Newtonian fluid, and this well agrees with previous research by Charunyakorn et al. [46]. Fig. 10 shows the relationship of shear stress and shear rate for the MPCs of 25% at 5 °C and 30 °C, at which the PCMs are at solid phase and liquid phase, respectively. It is observed that the rheological behaviors will not be influenced by the PCM phase change process since the polymer shell of the microcapsules is always in contact with the carrying fluid (not the PCM content inside the shell). The dynamic viscosity of MPCs is very important for its flow behaviors. In this paper, the viscosities of samples at different temperatures and concentrations were measured by rheometer. Fig. 11 shows the viscosities of MPCMs vs. shear rates for the product of DPNT06-0182 CIBA at a given concentration 35% but at different temperatures. The viscosity decreases as the temperature rises, as expected. Also the viscosity exhibit a little shear thinning effect, namely, it decreases with increasing shear rate. Overall the MPCs can be considered as Newtonian fluid after  $200 \text{ s}^{-1}$  shear rate, which is the minimal mean shear rate in the heat transfer experiment because the dynamic viscosity values are constant as the shear rates change. Fig. 12 shows the viscosity of slurries with different particle concentrations at a given temperature of 5 °C. As expected, the viscosity is higher with a higher concentration. Fig. 13 presents the results for the product of DS 5008X BASF at concentration of 25%. Similar trend is observed. Fig. 14 examines the particle size effect on the viscosity of MPCs for a given particle concentration and a given test temperature. The results show that the viscosity is higher for bigger particle slurries. Bearing in mind, the increase of viscosity will increase pump energy consumption, which will reduce the positive effect.

#### **4. Conclusions**

Experimental investigations have been carried out to investigate two different kinds of microencapsulated phase change materials (MPCMs) in terms of their thermal and rheological properties. The results showed that most of the microcapsules were spherical shaped and had smooth surfaces, and the structure analysis demonstrated that MPCMs had been successfully fabricated by their manufacturers. Particle size distribution (CIBA sample: 10 to 100  $\mu\text{m}$ ; BASF sample: 1 to 20  $\mu\text{m}$ ) was quite satisfactory for using these microcapsules in thermal energy storage and heat transfer. The heat of fusion of the two samples was 102 kJ/kg and 97 kJ/kg, respectively. Both

samples showed very good thermal stability. Nevertheless, prevention of supercooling crystallization phenomena of MPCM still needs more intensive research, such as how to enhance the contents of materials in the fabrication process. In this paper, there were three kinds of MPCs were prepared for each sample with the mass ratio of MEPCM to water and surfactant: 10:90:1, 25:75:1, 35:65:1, respectively. The addition of water did not change the melting temperature and crystallizing temperature of the MPCs samples. However, it changes the latent heat storage capacity of MPCMs and it increases gradually with the mass concentration of the MPCs. Overall the thermal conductivity and the specific heat of MPCs decrease with particle concentration for the temperatures below the melting point. The dynamic viscosity of slurries decreases with the temperature rising. Overall the MPCs can be considered as Newtonian fluid within the test region (shear rate  $>200 \text{ s}^{-1}$  and mass fraction  $<0.35$ ). The viscosity is higher for bigger particle slurries. Finally, the results concluded that MPCM have good potential for thermal energy storage purposes and it could be used for solar space heating as well.

### **Acknowledgement**

This work is supported by the UK Engineering and Physical Science Research Council (EPSRC grant number: EP/F061439/1), the National Natural Science Foundation of China (Grant No: 51071184). The authors are thankful to the Ciba Specialty Chemicals, UK, and the BASF, Germany, for supplying samples. The authors are also thankful to the Birmingham Science City: Energy Efficiency and Demand Project (Project Ref: SY/SP8008).

### **References**

- [1] S.S. Al-Jandal, A.A.M. Sayigh, Thermal performance characteristics of STC system with Phase Change Storage, *Renewable Energy*, 5 (1994) 390-399.
- [2] A. Hasan, A.A. Sayigh, Some fatty acids as phase-change thermal energy storage materials, *Renewable Energy*, 4 (1994) 69-76.
- [3] A. Karaipekli, A. SarI, Capric-myristic acid/expanded perlite composite as form-stable phase change material for latent heat thermal energy storage, *Renewable Energy*, 33 (2008) 2599-2605.

- [4] Y. Cai, Q. Wei, F. Huang, S. Lin, F. Chen, W. Gao, Thermal stability, latent heat and flame retardant properties of the thermal energy storage phase change materials based on paraffin/high density polyethylene composites, *Renewable Energy*, 34 (2009) 2117-2123.
- [5] F. Agyenim, P. Eames, M. Smyth, Experimental study on the melting and solidification behaviour of a medium temperature phase change storage material (Erythritol) system augmented with fins to power a LiBr/H<sub>2</sub>O absorption cooling system, *Renewable Energy*, 36 (2011) 108-117.
- [6] C.Y. Zhao, W. Lu, Y. Tian, Heat transfer enhancement for thermal energy storage using metal foams embedded within phase change materials (PCMs), *Solar Energy*, 84 (2010) 1402-1412.
- [7] C.Y. Zhao, Z.G. Wu, Heat Transfer Enhancement of High-Temperature Thermal Energy Storage Using Porous Materials, *Solar Energy Materials and Solar Cells*, Accepted, in press. , (2010).
- [8] C.Y. Zhao, D. Zhou, Z.G. Wu, Heat Transfer Enhancement of Phase Change Materials (PCMs) in Low and High Temperature Thermal Storage by Using Porous Materials, *International Heat Transfer Conference-14*, 8-13 August, Washington, D. C., USA. .
- [9] A. Karaipekli, A. SarI, K. Kaygusuz, Thermal conductivity improvement of stearic acid using expanded graphite and carbon fiber for energy storage applications, *Renewable Energy*, 32 (2007) 2201-2210.
- [10] A. SarI, K. Kaygusuz, Some fatty acids used for latent heat storage: thermal stability and corrosion of metals with respect to thermal cycling, *Renewable Energy*, 28 (2003) 939-948.
- [11] A. Sharma, V.V. Tyagi, C.R. Chen, D. Buddhi, Review on thermal energy storage with phase change materials and applications, *Renewable and Sustainable Energy Reviews*, 13 (2009) 318-345.
- [12] H. Zhang, X. Wang, Fabrication and performances of microencapsulated phase change materials based on n-octadecane core and resorcinol-modified melamine-formaldehyde shell, *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 332 (2009) 129-138.
- [13] J.L. J Choi, JH Kim, H Yang Preparation of microcapsules containing phase change materials as heat transfer media by in-situ polymerization, *Journal of Industrial and Engineering Chemistry* 7(2001) 358-362.
- [14] J.-S. Cho, A. Kwon, C.-G. Cho, Microencapsulation of octadecane as a phase-change material by interfacial polymerization in an emulsion system, *Colloid & Polymer Science*, 280 (2002) 260-266.
- [15] M.N.A. Hawlader, M.S. Uddin, H.J. Zhu, Encapsulated phase change materials for thermal energy storage: Experiments and simulation, *International Journal of Energy Research*, 26 (2002) 159-171.
- [16] M.N.A. Hawlader, M.S. Uddin, M.M. Khin, Microencapsulated PCM thermal-energy storage system, *Applied Energy*, 74 (2003) 195-202.
- [17] Y.F. Fan, X.X. Zhang, X.C. Wang, J. Li, Q.B. Zhu, Super-cooling prevention of microencapsulated phase change material, *Thermochimica Acta*, 413 (2004) 1-6.
- [18] X.X. Zhang, Y.F. Fan, X.M. Tao, K.L. Yick, Fabrication and properties of microcapsules and nanocapsules containing n-octadecane, *Materials Chemistry and Physics*, 88 (2004) 300-307.
- [19] E.Y. Kim, H.D. Kim, Preparation and properties of microencapsulated octadecane with waterborne polyurethane, *Journal of Applied Polymer Science*, 96 (2005) 1596-1604.

- [20] Y.-H. Tseng, M.-H. Fang, P.-S. Tsai, Y.-M. Yang, Preparation of microencapsulated phase-change materials (MCPCMs) by means of interfacial polycondensation, *Journal of Microencapsulation*, 22 (2005) 37-46.
- [21] Y. Özönur, M. Mazman, H.Ö. Paksoy, H. Evliya, Microencapsulation of coco fatty acid mixture for thermal energy storage with phase change material, *International Journal of Energy Research*, 30 (2006) 741-749.
- [22] C. Alkan, A. SarI, A. Karaiepli, O. Uzun, Preparation, characterization, and thermal properties of microencapsulated phase change material for thermal energy storage, *Solar Energy Materials and Solar Cells*, 93 (2009) 143-147.
- [23] R. Yang, Y. Zhang, X. Wang, Y. Zhang, Q. Zhang, Preparation of n-tetradecane-containing microcapsules with different shell materials by phase separation method, *Solar Energy Materials and Solar Cells*, 93 (2009) 1817-1822.
- [24] G.H. Zhang, C.Y. Zhao, Thermal and Rheological Properties of Microencapsulated Phase Change Material Slurries, 5th International Renewable Energy Storage Conference IRES 2010 , Invited Keynote paper, Berlin, Germany. .
- [25] C. Alkan, A. SarI, A. Karaiepli, Preparation, thermal properties and thermal reliability of microencapsulated n-eicosane as novel phase change material for thermal energy storage, *Energy Conversion and Management*, 52 (2011) 687-692.
- [26] A. SarI, C. Alkan, A. Karaiepli, Preparation, characterization and thermal properties of PMMA/n-heptadecane microcapsules as novel solid-liquid microPCM for thermal energy storage, *Applied Energy*, 87 (2010) 1529-1534.
- [27] A. SarI, C. Alkan, A. Karaiepli, O. Uzun, Microencapsulated n-octacosane as phase change material for thermal energy storage, *Solar Energy*, 83 (2009) 1757-1763.
- [28] Y.G. Bryant, Melt Spun Fibers Containing Microencapsulated Phase Change Material Proceedings, ASME Symposium, 44 (1999) 225-234.
- [29] X.X. Zhang, X.C. Wang, X.M. Tao, K.L. Yick, Energy storage polymer/MicroPCMs blended chips and thermo-regulated fibers, *Journal of Materials Science*, 40 (2005) 3729-3734.
- [30] N. Sarier, E. Onder, The manufacture of microencapsulated phase change materials suitable for the design of thermally enhanced fabrics, *Thermochimica Acta*, 452 (2007) 149-160.
- [31] E. Onder, N. Sarier, E. Cimen, Encapsulation of phase change materials by complex coacervation to improve thermal performances of woven fabrics, *Thermochimica Acta*, 467 (2008) 63-72.
- [32] P. Schossig, H.M. Henning, S. Gschwander, T. Haussmann, Micro-encapsulated phase-change materials integrated into construction materials, *Solar Energy Materials and Solar Cells*, 89 (2005) 297-306.
- [33] L.F. Cabeza, C. Castellón, M. Nogués, M. Medrano, R. Leppers, O. Zubillaga, Use of microencapsulated PCM in concrete walls for energy savings, *Energy and Buildings*, 39 (2007) 113-119.
- [34] C. Castellón, P. M. Medrano, P. J. Roca, P. M. Nogués, A. Castell, P. L.F. Cabeza, Use of Microencapsulated Phase Change Materials in Building Applications, *Buildings X*, (2007).
- [35] S.H. Lee, S.J. Yoon, Y.G. Kim, Y.C. Choi, J.H. Kim, J.G. Lee, Development of building materials by using micro-encapsulated phase change material, *Korean Journal of Chemical Engineering*, 24 (2007) 332-335.
- [36] C. Castellón, M. Medrano, J. Roca, L.F. Cabeza, M.E. Navarro, A.I. Fernández, A. Lázaro, B. Zalba, Effect of microencapsulated phase change material in sandwich panels, *Renewable Energy*, 35 (2010) 2370-2374.

- [37] P. Zhang, Z.W. Ma, R.Z. Wang, An overview of phase change material slurries: MPCs and CHS, *Renewable and Sustainable Energy Reviews*, 14 (2010) 598-614.
- [38] M. Goel, S.K. Roy, S. Sengupta, Laminar forced convection heat transfer in microencapsulated phase change material suspensions, *International Journal of Heat and Mass Transfer*, 37 (1994) 593-604.
- [39] S.K. Roy, B.L. Avanic, Laminar forced convection heat transfer with phase change material emulsions, *International Communications in Heat and Mass Transfer*, 24 (1997) 653-662.
- [40] Y. Yamagishi, H. Takeuchi, A.T. Pyatenko, N. Kayukawa, Characteristics of microencapsulated PCM slurry as a heat-transfer fluid, *AIChE Journal*, 45 (1999) 696-707.
- [41] J.L. Alvarado, C. Marsh, C. Sohn, G. Phetteplace, T. Newell, Thermal performance of microencapsulated phase change material slurry in turbulent flow under constant heat flux, *International Journal of Heat and Mass Transfer*, 50 (2007) 1938-1952.
- [42] X. Wang, J. Niu, A.H.C. van Paassen, Raising evaporative cooling potentials using combined cooled ceiling and MPCM slurry storage, *Energy and Buildings*, 40 (2008) 1691-1698.
- [43] B.M. Diaconu, S. Varga, A.C. Oliveira, Experimental study of natural convection heat transfer in a microencapsulated phase change material slurry, *Energy*, 35 (2010) 2688-2693.
- [44] X. Wang, J. Niu, Y. Li, X. Wang, B. Chen, R. Zeng, Q. Song, Y. Zhang, Flow and heat transfer behaviors of phase change material slurries in a horizontal circular tube, *International Journal of Heat and Mass Transfer*, 50 (2007) 2480-2491.
- [45] X.-X. Zhang, Y.-F. Fan, X.-M. Tao, K.-L. Yick, Crystallization and prevention of supercooling of microencapsulated n-alkanes, *Journal of Colloid and Interface Science*, 281 (2005) 299-306.
- [46] P. Charunyakorn, S. Sengupta, S.K. Roy, Forced convection heat transfer in microencapsulated phase change material slurries: flow in circular ducts, *International Journal of Heat and Mass Transfer*, 34 (1991) 819-833.